



Canadian Induracoat Corporation
 Vancouver - Calgary - Victoria
 toll free:1.855.652.0812
 www.induracoat.com

GELFLEX® Chemical Resistance-

ASTM D3912 - modified 21 day immersion exposure			
The information in this chart is intended to only as a guide. This information has been compiled from various sources believed to be reliable. To verify compatibility or suitability of this product in specific applications, the product should be tested under the specific service conditions. The ratings are for resistance at 77° F unless otherwise noted. Recommended Conditional means there may be some effect: swelling, discoloration, cracking. Wash down within one hour of spillage to avoid effects.			
Recommended	R		
Recommended/Conditional	RC		
Not Recommended	NR		
Test Media:	Result:	Test Media:	Result:
Acetic Acid, 100%	NR	Motor Oil	R
Acetone	RC	MTBE	RC
Ammonium Hydroxide, 20%	R	MTBE (5%)/gasoline	RC
Antifreeze/Water	RC	Muriatic Acid (10% HCL)	R
Brake Fluid (DOT 3)	RC	NaCl (10%)/water	R
Bromine	R		
Chlorine	R		
Clorox 10%/water	RC	Phosphoric Acid (10%)	R
Diesel Fuel	R	Potassium Hydroxide (10%)	R
Gasoline	R	Skydrol	RC
Hydrochloric Acid (10%)	RC	Sodium Hydroxide (50%)	R
Hydrofluoric Acid (10%)	RC	Sodium Bicarbonate	R
Hydraulic Fluid	RC	Sugar/Water	R
Isopropyl Alcohol	R	Sulfuric Acid (10%)	R
Lactic Acid	R	Sulfuric Acid (50%)	RC
MEK	RC	Toluene	R
Methanol	RC	Vinegar (5%)/water	R
		Water (180° F)	R